

# **EnergyCell RE Front Terminal Battery**

**VRLA Battery for Renewable Energy Storage** 

- Front Terminal Access Design for Ease of Maintenance and Installation
- High-Density Pasted Plates for High Cycle Life
- Lead-Calcium-Tin Alloy Plates for Long Life in Both Cycling and Float Applications
- High Recharge Efficiency
- Compact Footprint for Higher Energy Density Requirements
- Thermally Welded Case-to-Cover Bond to Eliminate Leakage
- UL-Recognized Component



The EnergyCell RE Valve Regulated Lead Acid (VRLA) battery is designed for high power density and renewable energy cycling applications. Absorbed Glass Matt (AGM) technology provides for efficient gas recombination of up to 99% and freedom from electrolyte maintenance. The EnergyCell RE also features low profile terminals with threaded copper alloy inserts providing reduced maintenance and increased safety.



## **EnergyCell RE Front Terminal Battery Specifications**

EnergyCell 170RE	EnergyCell 200RE	
6	6	
12 VDC	12 VDC	
Discharge: -40 to 71°C (-40 to 160°F) Charge: -23 to 60°C (-10 to 140°F)		
23 to 27°C (74 to 80°F)		
25 Amps DC	30 Amps DC	
13.62 VDC / unit average at 25°C (77°F)		
14.4 VDC / unit average at 25°C (77°F)		
Battery can be stored up to 18 months at 25°C (77°F) before a freshening charge is required. Batteries stored at temperatures greater than 25°C (77°F) will require recharge sooner than batteries stored at lower temperatures.		
5mV per degree C per cell (2V)		
Threaded copper alloy insert terminal to accept 1/4"-20 UNC bolt		
110 in-lbs (12.4 Nm)		
115 lbs (52 kg)	131 lbs (60 kg)	
11.14 x 22.01 x 4.95" (28.3 x 55.9 x 12.6 cm)	12.60 x 22.01 x 4.95" (32.0 x 55.09 x 12.6 cm)	
	6 12 VDC  Discharge: -40 Charge: -23 to 27  23 to 27  25 Amps DC  13.62 VDC / unit  14.4 VDC / unit  Battery can be stored up to 18 months at 25°C (77°F) temperatures greater than 25°C (77°F) will require resomic 5mV per deg  Threaded copper alloy insert  110 in-	


<sup>\*</sup> Batteries to be installed with 0.5 in (12.7 mm) spacing minimum and free air ventilation


#### Ampere Hour Capacity to 1.75 Volts Per Cell at 77°F (25°C)

Discharge in Hours	EnergyCell 170RE	EnergyCell 200RE
1	89.1	103.0
3	114.2	132.0
4	120.6	139.6
5	125.9	145.5
8	137.0	158.4

Discharge in Hours	EnergyCell 170RE	EnergyCell 200RE
12	145.3	168.0
20	153.8	178.0
24	157.0	181.4
48	163.9	189.6
100	170.0	200.0

Specifications subject to change without notice





### **Available From:**



#### Corporate Office:

17825 59th Ave. NE, Suite B Arlington, WA 98223 USA Phone: +1 360 435 6030 Fax: +1 360 435 6019

#### **European Office:**

Hansastrasse 8 D-91126 Schwabach, Germany Phone: +49 9122 79889 0 Fax: +49 9122 79889 21

## Asia Office:

Suite 1903, Tower 1, China Hong Kong City 33 Canton Road, Kowloon Hong Kong

Phone: +852 2736 8663 Fax: +852 2199 7988

## Latin American Office:

15105 Cedar Bluff Pl. Wellington, FL 33414 USA Phone: +1 561 792 9651 Fax: +1 561 792 7157